



AISLAGLAS 4/CAMARA/4	TRANSMISIÓN VISUAL	REFLEXIÓN VISUAL	FACTOR SOLAR	Emisividad capa	VALOR U SEGÚN CAMARA (ARGON 90%)					
					CAM.06	CAM.08	CAM.10	CAM.12	CAM.14	CAM.16
D.ACRIST. CON VIDRIOS FLOAT	0,81	0,15	0,77	NO	3,3 (3,1)	3,1 (2,9)	3,0 (2,8)	2,9 (2,7)	2,8 (2,6)	2,7 (2,6)
SUNGUARD NEUTRAL 67	0,61	0,2	0,6	NO	3,3 (3,0)	3,1 (2,8)	2,9 (2,7)	2,8 (2,6)	2,7 (2,6)	2,7 (2,6)
SUNGUARD LIGHT BLUE 52	0,47	0,15	0,45	NO	3,2 (2,9)	3,0 (2,7)	2,8 (2,6)	2,7 (2,5)	2,6 (2,5)	2,6 (2,4)
SUNGUARD SILVER GREY 32	0,29	0,23	0,3	NO	2,1 (2,8)	2,8 (2,6)	2,6 (2,4)	2,5 (2,3)	2,4 (2,2)	2,4 (2,2)
SUNGUARD ROYAL BLUE 20	0,2	0,18	0,25	NO	3,0 (2,6)	2,7 (2,4)	2,5 (2,3)	2,4 (2,2)	2,3 (2,1)	2,2 (2,1)
SUNGUARD SILVER 20	0,2	0,35	0,21	NO	3,0 (2,7)	2,7 (2,4)	2,5 (2,3)	2,4 (2,2)	2,3 (2,1)	2,2 (2,1)